



30° HELIX END MILLS - CARBIDE TECHNICAL INFORMATION

YOUR #1 SOURCE FOR AMERICAN-MADE PREMIUM QUALITY CUTTING TOOLS

THESE SFM VALUES ARE FOR UNCOATED TOOLS.
FOR COATED TOOLS INCREASE SFM: TICN = +25% ALTIN = +40%

SFM FOR GENERAL PURPOSE CARBIDE END MILLS

MATERIAL / TYPE	Rc HARDNESS	2 Flute 30° Helix Stub, Reg	2 Flute 30° Helix Long, X-Long	4 Flute 30° Helix Stub, Reg	4 Flute 30° Helix Long, X-Long
COBALT BASE ALLOYS					
STELLITE, HS-21, HAYNES 25/188, X-40, L-605	UNDER 32 OVER 32	- -	- -	175 - 225 125 - 175	150 - 200 100 - 150
NICKEL BASE ALLOYS					
INCONEL-625/718, WASPALLOY, RENE, HASTELLOY	UNDER 32 OVER 32	- -	- -	125 - 175 70 - 115	100 - 150 70 - 100
IRON BASE ALLOYS					
INCOLOY 800-802, MULTIMET N-155, TIMKIN 16-25-6, CARPENTER 22-b3	UNDER 32 OVER 32	- -	- -	175 - 225 125 - 175	150 - 200 100 - 150
MONEL					
MONEL-65% NICKEL	-	175 - 300	125 - 175	175 - 300	125 - 175
TITANIUM ALLOYS					
COMMERCIALLY PURE, 6Al-4V, ASTM 1/2/3, 6Al-25N-4Zr-2Mo-Si	- -	200 - 300 -	125 - 250 -	200 - 300 -	125 - 250 -
STAINLESS STEEL (PRECIPITATION)					
12/8, 15/5, 17/4, AM-350/355	UNDER 32 OVER 32	- -	- -	150 - 250 125 - 175	100 - 150 80 - 150
STAINLESS STEEL (AUSTENITIC)					
200 SERIES, 302, 303, 304, 316	UNDER 32 OVER 32	- -	- -	200 - 250 150 - 200	125 - 175 100 - 150
STAINLESS STEEL (AUSTENITIC)					
304L, 316L	UNDER 32 OVER 32	- -	- -	90 - 125 75 - 110	80 - 120 60 - 90
STAINLESS STEEL (MARTENSITIC)					
403, 410, 416, 440	UNDER 32 OVER 32	- -	- -	150 - 250 125 - 175	100 - 150 80 - 150
HIGH STRENGTH TOOL STEELS					
4140, 4340, 6150, 5210, A2, D2, P20, H11, H13, S2, 01	UNDER 32 OVER 32	- -	- -	150 - 225 60 - 125	125 - 175 80 - 120
MEDIUM ALLOY STEELS					
200, 250, 300	UNDER 32 OVER 32	- -	- -	200 - 250 125 - 175	150 - 200 100 - 150
CARBON STEELS					
1000's, 1100's, 1300's	UNDER 32 OVER 32	- -	- -	200 - 250 125 - 175	150 - 200 100 - 150
DUCTILE					
DUCTILE CAST IRONS	-	250 - 350	200 - 300	300 - 400	200 - 300
CAST IRONS					
GRAY CAST IRONS	-	225 - 325	175 - 250	250 - 350	175 - 250
ALUMINUM					
2014, 2024, 6061-(T1-T6) 7075, DIE CAST, EXTRUDED	- -	500 min. -	500 min. -	500 min. -	500 min. -
MAGNESIUM					
	-	500 min.	500 min.	500 min.	500 min.
COPPER, COPPER ALLOYS					
	-	400 - 500	400 - 500	300 - 400	250 - 350
BRASS BRONZE					
BRASS, ALUM/BRONZE, LOW SILICON BRONZE	- -	300 - 400 -	300 - 400 -	250 - 350 -	200 - 300 -
COMPOSITES					
G-10 FIBERGLASS, GRAPHITE, GRAPHITE/EPOXY, PLASTICS	- -	250 - 1000 -	250 - 1000 -	250 - 1000 -	250 - 1000 -

30° HELIX END MILLS - CARBIDE TECHNICAL INFORMATION



YOUR #1 SOURCE FOR AMERICAN-MADE PREMIUM QUALITY CUTTING TOOLS

MILLING

I.P.T. (INCH PER TOOTH) FOR GENERAL PURPOSE CARBIDE END MILLS						
MATERIAL / TYPE	Rc HARDNESS	UP TO 1/8"	1/8" - 1/4"	1/4" - 1/2"	1/2" - 1"	1" - 1-1/4"
COBALT BASE ALLOYS						
STELLITE, HS-21,	UNDER 32	.0005"-.0010"	.0005"-.0010"	.0008"-.0020"	.0020"-.0040"	.0030"-.0050"
HAYNES 25/188, X-40, L-605	OVER 32	.0003"-.0005"	.0003"-.0005"	.0005"-.0015"	.0010"-.0030"	.0020"-.0040"
NICKEL BASE ALLOYS						
INCONEL-625/718, WASPALLOY,	UNDER 32	.0005"-.0010"	.0005"-.0010"	.0008"-.0020"	.0020"-.0040"	.0030"-.0050"
RENE, HASTELLOY	OVER 32	.0003"-.0005"	.0003"-.0005"	.0005"-.0015"	.0010"-.0030"	.0020"-.0040"
IRON BASE ALLOYS						
INCOLOY 800-802, MULTIMET N-155,	UNDER 32	.0005"-.0010"	.0005"-.0010"	.0008"-.0020"	.0020"-.0040"	.0030"-.0050"
TIMKIN 16-25-6, CARPENTER 22-b3	OVER 32	.0003"-.0005"	.0003"-.0005"	.0005"-.0015"	.0010"-.0030"	.0020"-.0040"
MONEL						
MONEL-65% NICKEL	-	.0007"-.0015"	.0007"-.0015"	.0010"-.0025"	.0030"-.0050"	.0040"-.0060"
TITANIUM ALLOYS						
COMMERCIALLY PURE, 6Al-4V,	-	.0007"-.0015"	.0007"-.0015"	.0010"-.0025"	.0030"-.0050"	.0040"-.0060"
ASTM 1/2/3, 6Al-25N-4Zr-2Mo-Si	-	-	-	-	-	-
STAINLESS STEEL (PRECIPITATION)						
12/8, 15/5, 17/4, AM-350/355	UNDER 32	.0005"-.0010"	.0005"-.0010"	.0008"-.0020"	.0020"-.0040"	.0030"-.0050"
	OVER 32	.0003"-.0005"	.0003"-.0005"	.0005"-.0015"	.0010"-.0030"	.0020"-.0040"
STAINLESS STEEL (AUSTENITIC)						
200 SERIES, 302, 303, 304, 316	UNDER 32	.0005"-.0010"	.0005"-.0010"	.0008"-.0020"	.0020"-.0040"	.0030"-.0050"
	OVER 32	.0003"-.0005"	.0003"-.0005"	.0005"-.0015"	.0010"-.0030"	.0020"-.0040"
STAINLESS STEEL (AUSTENITIC)						
304L, 316L	UNDER 32	.0005"-.0008"	.0005"-.0008"	.0008"-.0015"	.0015"-.0030"	.0020"-.0040"
	OVER 32	.0003"-.0005"	.0003"-.0005"	.0005"-.0010"	.0010"-.0020"	.0015"-.0030"
STAINLESS STEEL (MARTENSITIC)						
403, 410, 416, 440	UNDER 32	.0005"-.0010"	.0005"-.0010"	.0008"-.0020"	.0020"-.0040"	.0030"-.0050"
	OVER 32	.0003"-.0005"	.0003"-.0005"	.0005"-.0015"	.0010"-.0030"	.0020"-.0040"
HIGH STRENGTH TOOL STEELS						
4140, 4340, 6150, 5210, A2,	UNDER 32	.0005"-.0010"	.0005"-.0010"	.0008"-.0020"	.0020"-.0040"	.0030"-.0050"
D2, P20, H11, H13, S2, O1	OVER 32	.0003"-.0005"	.0003"-.0005"	.0005"-.0015"	.0010"-.0030"	.0020"-.0040"
MEDIUM ALLOY STEELS						
200, 250, 300	UNDER 32	.0007"-.0015"	.0007"-.0015"	.0010"-.0025"	.0030"-.0050"	.0040"-.0060"
	OVER 32	.0005"-.0010"	.0005"-.0010"	.0008"-.0020"	.0020"-.0040"	.0030"-.0050"
CARBON STEELS						
1000's, 1100's, 1300's	UNDER 32	.0007"-.0015"	.0007"-.0015"	.0010"-.0025"	.0030"-.0050"	.0040"-.0060"
	OVER 32	.0005"-.0010"	.0005"-.0010"	.0008"-.0020"	.0020"-.0040"	.0030"-.0050"
DUCTILE						
DUCTILE CAST IRONS	-	.0010"-.0020"	.0010"-.0020"	.0015"-.0040"	.0030"-.0100"	.0050"-.0100"
CAST IRONS						
GRAY CAST IRONS	-	.0010"-.0020"	.0010"-.0020"	.0015"-.0040"	.0030"-.0100"	.0050"-.0100"
ALUMINUM						
2014, 2024, 6061-(T1-T6)	-	.0010"-.0020"	.0010"-.0020"	.0015"-.0040"	.0030"-.0150"	.0050"-.0150"
7075, DIE CAST, EXTRUDED	-	-	-	-	-	-
MAGNESIUM						
	-	.0010"-.0020"	.0010"-.0020"	.0015"-.0040"	.0030"-.0100"	.0050"-.0100"
COPPER, COPPER ALLOYS						
	-	.0007"-.0015"	.0007"-.0015"	.0010"-.0025"	.0020"-.0080"	.0040"-.0100"
BRASS BRONZE						
BRASS, ALUM/BRONZE,	-	.0007"-.0015"	.0007"-.0015"	.0010"-.0025"	.0020"-.0080"	.0040"-.0100"
LOW SILICON BRONZE	-	-	-	-	-	-
COMPOSITES						
G-10 FIBERGLASS, GRAPHITE,	-	.0010"-.0020"	.0010"-.0020"	.0015"-.0040"	.0030"-.0100"	.0050"-.0100"
GRAPHITE/EPOXY, PLASTICS	-	-	-	-	-	-

TECHNICAL